

3/8" SMARTCORE INDUSTRIAL PANEL

DESCRIPTION:

Our 3/8" Industrial Panel is composed of post industrial interlocking fibres impregnated with a water-repellent petroleum wax emulsion. It is coated on the front side with a smooth calendered clay coating and textured finished on the back side. Our 3/8" Industrial Panel is a product with good mechanical and laminating properties.

ENVIRONMENTAL CONSIDERATIONS:

Contains no carcinogenic formaldehyde, no urea formaldehyde, no volatile organic carbon (VOC), hydro-chlor-fluorocarbon (HCFC), pentane nor other harsh or toxic chemicals used for binding and waterproofing. Binding agent used in this product is a natural, abundant and renewable resource.

USES:

The 3/8" Industrial Panel is produced under strict specifications. It can be used for various industrial requirements. It's strength and smooth surface make this board ideal for tack boards, markerboards, black boards, cork boards, packaging, coating or laminating applications.

STORAGE:

The 3/8" Industrial Panel must be stored 100mm (4") above ground level. We strongly recommend storing the panel in an interior environment. However, if it's stored outside, it must be adequately protected from the elements with tarpaulins.

<u>DIMENSIONS AND PACKAGING</u>									
Width	Length	Tolerance	Panels/Bundle						
1219 mm (48")	Product is available in different lengths. contact our customer	-3.2 / +0 mm (-1/8", +0")	124						
1244 mm (49")	service department for available dimensions	-0 /+3.2mm (-0", +1/8")							

	<u>CHARACTERISTICS</u>	<u>UNITS</u>		<u>RESULTS</u>		TEST METHOD
		<u>METRIC</u>	<u>IMPERIAL</u>	<u>METRIC</u>	<u>IMPERIAL</u>	
	Thickness 9.53 mm (3/8")	%	%	+/-10%	+/-10%	ASTM C209
	Squareness	mm	in	3.2	.125	Mfg Test Method
r F 1	Face trueness	mm	in	12.5	0.5	Mfg Test Method
	Thermal Resistance, 25.4 mm (1")	RSI	R	0.52	3.0	ASTM C209
	Transverse Load at Rupture min	N	lbf	36	8	ASTM C209
	Tensile Strength - Parallel to surface	kPa	lb/in2	2819.3	408.9	ASTM C209
	Water Absorption 2 hr	%	%	15.4	15.4	ASTM C209
	Linear Moisture Expansion	%	%	<0.5	<0.5	ASTM D1037

ADDITIONAL INFORMATION

Color variation may occur from one production to the next, however this does not affect the panel's performance.

APPLICABLE STANDARDS

Not applicable

CERTIFICATIONS

The 3/8" Industrial Panel contributes to credits in order to obtain a LEED certification. Some panels within our product line are also available FSC Mix Credit certified. Please Contact us for more information.